



**TÜBİTAK
BURSA TEST AND ANALYSIS LABORATORY**

BUTAL
GT20200157- 1
25/08/2020

Page 1 / 2

TEST REPORT

Customer Name/Address LTD NOVA / R. Agladze Sok. 0119 / N 45 Tiflis / GÜRCİSTAN

T/F:() --/ / () --

Order Date/No : 13/07/2020

Sample Description : Production of Plastic (Polythene) Water Tanks 100-10000 lt, Silindroid, Vertical and Open Shaped Single Layered White

Sample Receipt Date :25/08/2020

Sample Delivered by: Cargo Delivery

Number of Pages: 2

Remarks : Sampling and identification of the sample was done by the customer. This report has been prepared as a revised version of the report GT20200157 due to inadvertent writing of the sample description, (1000 instead of 10000) by the customer. The report numbered GT20200157 dated 18/08/2020 is invalid.

*Test results, methods measurement uncertainty (if applicable, given in 95% confidence interval) and other information are given on the following pages which are part of this report.

*This report and results can not be used for the purpose of advertising by the requesting client.

*This report has been given as a full content and can not be copied by sections. This report can not be reproduced without prior written approval of TÜBİTAK BUTAL.

* In case the information provided by the customer, TÜBİTAK BUTAL will not be responsible for this information.

* In case of sampling by customer the results in this report refer only to samples tested

* In case of sampling by customer, the sampling uncertainty were not included to the uncertainty budget.

* Test marked with (D) refers the test provided by external sources.

* Testing reports without signature are not valid.

DATE
25/08/2020

e-signature
Nejdet OGAN
Deputy Person in Charge of
Laboratories

e-signature
Sedat AKTAŞ
Director

This document has been signed by e-signature.
The document can be verified via the link " <https://butalonlinetest.tubitak.gov.tr/butalOnline> " using the code "HW33312478/4'05D"

REVISED REPORT

Test Date : 07-18.08.2020

Sample Identification : Production of Plastic (Polythene) Water Tanks 100-10000 lt, Silindroid,
Vertical and Open Shaped Single Layered White

Parameter	Unit	Test Method	Test Result Mean \pm s	Limit Value
Total Migration (in Water) at 40°C ,10 days	mg/dm ²	TS EN 1186 -3	< 1	10
Total Migration (Asetic Acid %3) at 40°C ,10 days	mg/dm ²	TS EN 1186 -3	< 1	10
Total Migration (Ethanol %10) at 40°C ,10 days	mg/dm ²	TS EN 1186 -3	< 1	10
Total Fat Migration (Ethanol %95) at 50°C ,1 days	mg/dm ²	TS EN 1186-15	< 1	10

The limit value is taken from Turkish Food Codex Communiqué on Plastic Materials and Articles in Contact with Food (Communiqué No : 2019/44).

The reported results are in accordance with the commission code of "Food Contact Plastics and Materials" numbered 10/2011/EU, which is included in the code of European Parliament and the Council on the Substance and Material Contacted with Food numbered 1935 /2004/EC.