TÜBİTAK
BUTAL

BUTAL
GT20260290
10-26

TÜBİTAK
BURSA TEST AND ANALYSIS LABORATORY

TEST REPORT

Customer Name/Address NOVA LLC / Tbilisi Didube District, R.Agladze Str. / Tbilisi / Georgia

T/F:() --/ /

Order Date/No : 26/06/2026

Sample Description : Water Tanks: 20 / 30 / 40 / 60 / 120 / 220 Lt Double Layer (Blue / White)

Sample Receipt Date :25/09/2026 **Sample Delivered by**: Cargo Delivery

Number of Pages: 2

Remarks : Sampling and identification of the sample was done by the customer.

*Test results, methods measurement uncertainty (if applicable, given in 95% confidence interval) and other information are given on the following pages which are part of this report.
*This report and results can not be used for the purpose of advertising by the requesting client.
*Since this report is given as a full content, it cannot be quoted in sections from the report, and the report cannot be copied or reproduced.
* In case the information provided by the customer, TÜBİTAK BUTAL will not be responsible for this information.
* In case of sampling by customer the results in this report refer only to samples tested
* In case of sampling by customer, the sampling uncertainty were not included to the uncertainty budget.
* Test marked with (D) refers the test provided by external sources.
* Testing reports without e-signature are not valid.

Date		
06/10/2026	*e-signature*	*e-signature*
	YİĞİT ŞAHİN	SEDAT AKTAŞ
	Person in Charge of Laboratories	Director

This document has been signed by e-signature.
The document can be verified via the link " https://butalonlinetest.tubitak.gov.tr/butalOnline " using the code “HW333733:3'03N”

Gaziakdemir Mahallesi Stadyum Cadde No:11 Osmangazi/ BURSA
T. +90 224 233 94 40 F.+90 224 94 45 - +90 224 234 57 06
www.butal.tubitak.gov.tr e-mail:butal@tubitak.gov.tr

Test Date : 25.09-06.10.2026

Sample Identification : Water Tanks 20 / 30 / 40 / 60 / 120 / 220 Lt Double Layer (Blue / White)

Parameter	**Unit**	**Test Method**	**Test Result Mean ± sd**	**Limit Value[1]**	**Conformity[2]**
Total Migration *(Acetic Acid %3) at 40˚C,10 days*	mg/dm^2	TS EN 1186-3: 2022	8,20 ± 0,14	10	Pass
Total Migration *(Ethanol %10) at 40˚C, 10 days*	mg/dm^2	TS EN 1186-3: 2022	< 1	10	Pass
Total Migration *(Ethanol %20) at 40˚C, 10 days*	mg/dm^2	TS EN 1186-3: 2022	1,55 ± 0,07	10	Pass
Total Migration *(Ethanol %50) at 40˚C, 10 days*	mg/dm^2	TS EN 1186-3: 2022	2,80 ± 0,14	10	Pass
Total Fat Migration *(Ethanol %95) at 50˚C, 1 day*	mg/dm^2	TS EN 1186-3: 2022	< 1	10	Pass

1) The limit value is taken from Turkish Food Codex Communiqué on Plastic Materials and Articles in Contact with Food (Communiqué No : 2019/44).

2) While choosing the decision rule used in conformity assessment, " Guideline on declaration of conformity to ILAC G8 Specification" was taken as reference.